




## ARKA GOLDEN 11,6X11,6

| REFERENCE      | SIZE (cm) | THICKNESS (mm) | GROUP     |
|----------------|-----------|----------------|-----------|
| <b>A045085</b> | 11,6x11,6 | 8,00           | PC BIA GL |

### DIMENSIONS AND SURFACE PROPERTIES

|                                                             |              |                                  |
|-------------------------------------------------------------|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|-------------------------------------------------------------|--------------|----------------------------------|

### PHYSICAL PROPERTIES

|                           |                 |                         |
|---------------------------|-----------------|-------------------------|
| Water absorption capacity | EN ISO 10545-03 | < 0,5%                  |
| Flexion resistance        | EN ISO 10545-04 | => 35 N/mm <sup>2</sup> |
| Thermal shock resistance  | EN ISO 10545-09 | It stands the test      |
| Cracking resistance       | EN ISO 10545-11 | It stands the test      |
| Frost resistance          | EN ISO 10545-12 | It stands the test      |

### CHEMICAL PROPERTIES

|                                                        |                 |      |
|--------------------------------------------------------|-----------------|------|
| Resistance to acids                                    | EN ISO 10545-13 | GLC  |
| Resistance to alcalis                                  | EN ISO 10545-13 | BGLC |
| Resistance to cleaning products                        | EN ISO 10545-13 | GA   |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA   |
| Stains resistance                                      | EN ISO 10545-14 | 5    |