


## REFRACTION WIND 7,5X30

| REFERENCE      | SIZE (cm) | THICKNESS (mm) | GROUP   |
|----------------|-----------|----------------|---------|
| <b>A036326</b> | 7,5X30    | 12,00          | REVESTI |



### DIMENSIONS AND SURFACE PROPERTIES

|                                                             |              |                                  |
|-------------------------------------------------------------|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|-------------------------------------------------------------|--------------|----------------------------------|

### PHYSICAL PROPERTIES

|                           |                 |                        |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10%                   |
| Flexion resistance        | EN ISO 10545-04 | => 20N/mm <sup>2</sup> |
| Thermal shock resistance  | EN ISO 10545-09 | It stands the test     |
| Cracking resistance       | EN ISO 10545-11 | It stands the test     |
| Frost resistance          | EN ISO 10545-12 | Not pass the test      |

### CHEMICAL PROPERTIES

|                                                        |                 |      |
|--------------------------------------------------------|-----------------|------|
| Resistance to acids                                    | EN ISO 10545-13 | 0.00 |
| Resistance to alcalis                                  | EN ISO 10545-13 | 0.00 |
| Resistance to cleaning products                        | EN ISO 10545-13 | GLA  |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance                                      | EN ISO 10545-14 | 5    |