

Technical characteristics report

Serial: Newport

Size: 31.6x31.6

NEWPORT ROJO

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: B1la

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III (1500 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport	Size: 31.6x31.6
-----------------	-----------------

NEWPORT AZUL

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: B1la

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III (750 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport

Size: 31.6x31.6

NEWPORT BEIGE

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: BIIa

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	IV (2100 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport

Size: 31.6x31.6

NEWPORT CENIZA

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: B1la

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III (1500 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport	Size: 31.6x31.6
-----------------	-----------------

NEWPORT CHOCOLATE

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: BIIa

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III (1500 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport	Size: 31.6x31.6
-----------------	-----------------

NEWPORT GRAFITO

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: BIIa

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III (1500 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport

Size: 31.6x31.6

NEWPORT MARINO

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: BIIa

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III (1500 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport	Size: 31.6x31.6
-----------------	-----------------

NEWPORT NEGRO

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: BIIa

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	II (600 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 4
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport	Size: 31.6x31.6
-----------------	-----------------

NEWPORT PERLA

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: Blla

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	IV (2100 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport

Size: 31.6x31.6

NEWPORT ROJO

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: B1la

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III (1500 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport

Size: 31.6x31.6

NEWPORT SLATEGREY

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: B1la

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III (1500 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 4
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

Technical characteristics report

Serial: Newport	Size: 31.6x31.6
-----------------	-----------------

NEWPORT TORTOLA

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: BIIa

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III (1500 rev)
Hardness degree, method MOHS	UNE 67-101-92	≥ 4
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5

APE

best for you

Technical characteristics report

Serial: Newport

Size: 31.6x31.6

NEWPORT PURPURA

Floor tiles with red body. Dry pressed ceramic tiles for interior floors and walls.

It accomplishes norm: UNE-EN 14411

Group: BIIa

Name, Test	European norm	Value
Size, thickness, side straightness, flatness, orthogonality	UNE-EN 14411	It accomplishes all requirements
Water absorption capacity	EN ISO 10545-03	$3\% < E \leq 6\%$
Flexion resistance	EN ISO 10545-04	$> 22 \text{ N/mm}^2$
Resistance to the abrasion, method PEI	EN ISO 10545-07	III
Hardness degree, method MOHS	UNE 67-101-92	≥ 5
Thermic impact resistance	EN ISO 10545-9	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Resistance to acids	EN ISO 10545-13	GHA
Resistance to bases	EN ISO 10545-13	GHA
Resistance to cleaning products and chemical products for swimming pool water	EN ISO 10545-13	GA
Stains resistance	EN ISO 10545-14	5